



Technical Datasheet

Satwax-5525

Analysis	Method	Unit	Typical
Congealing point	DIN ISO 2207	°C	73,0
Drop Point	ASTM D 3954	°C	80,6
Drop Point	ASTM D 127	°C	78,3
Needle penetration 25 °C	DIN 51 579	mm/10	24
Kin. Viscosity 100 °C	DIN EN ISO 3104	mm ² /s	14,90
Density 80 °C	DIN 51757 method 3	Kg/m ³	806,0
Content of oil	DIN 51531	Mass.-%	1,2
Content of oil	ASTM D 721	Mass.-%	1,2
Sulfur	DIN EN ISO 14596	% (m/m)	< 0,002
Colour Saybolt	ASTM D 156		22
Colour Saybolt	ASTM D 6045		22
Purity	FDA 172. 886		conform

The above mentioned data are only an indication and do not present any guarantee.

Any deviations of the data are no reason for claim.