



Technical Datasheet

Satwax-5525

Analysis	Method	Unit	Typical
Congealing point	DIN ISO 2207	°C	73,0
Drop Point	ASTM D 3954	°C	80,6
Drop Point	ASTM D 127	°C	78,3
Needle penetration 25 °C	DIN 51 579	mm/10	24
Kin. Viscosity 100 °C	DIN EN ISO 3104	mm ² /s	14,90
Density 80 °C	DIN 51757 method 3	Kg/m ³	806,0
Content of oil	DIN 51531	Mass.-%	1,2
Content of oil	ASTM D 721	Mass.-%	1,2
Sulfur	DIN EN ISO 14596	% (m/m)	< 0,002
Colour Saybolt	ASTM D 156		22
Colour Saybolt	ASTM D 6045		22
Purity	FDA 172. 886		conform

The above-mentioned data are only an indication and do not present any guarantee.

Any deviations of the data are no reason for claim.